



# Miramesh<sup>®</sup> TR

Miramesh<sup>®</sup> TR is composed of black high-tenacity polypropylene yarns that are woven together to produce an open mesh geotextile. Miramesh<sup>®</sup> TR is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D4595	lbs/ft (kN/m)	2100 (30.6)	2100 (30.6)
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	90	

Mechanical Properties	Test Method	Unit	Minimum Value
			MD
Creep Reduced Strength <sup>1</sup>	ASTM D5262	lbs/ft (kN/m)	686 (10.0)
Allowable Design Strength <sup>1</sup>	GRI GT-7	lbs/ft (kN/m)	594 (8.7)

<sup>1</sup> Allowable Design Strength values are for sand, silt and clay. Creep Reduction Factor based on 75-year design life.

Physical Properties	Unit	Roll Characteristic
Aperture Size (machine direction)	in (mm)	0.08 (2)
Aperture Size (cross machine direction)	in (mm)	0.12 (3)
Color	--	Black
Mass/Unit Area (ASTM D5261)	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	5.9 (200)
Roll Dimensions (width x length)	ft (m)	8 x 150 (2.4 x 45.7)
Roll Area	yd <sup>2</sup> (m <sup>2</sup> )	133 (110)
Estimated Roll Weight	lbs (kg)	52 (24)

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi<sup>®</sup> is a registered trademark of Nicolon Corporation.

Copyright © 2013 Nicolon Corporation. All Rights Reserved.