



**ROLLMAX™**  
ROLLED EROSION CONTROL

## Specification Sheet – EroNet™ SC150® Erosion Control Blanket

### DESCRIPTION

The extended-term double net erosion control blanket shall be a machine-produced mat of 70% agricultural straw and 30% coconut fiber with a functional longevity of up to 24 months. (NOTE: functional longevity may vary depending upon climatic conditions, soil, geographical location, and elevation). The blanket shall be of consistent thickness with the straw and coconut evenly distributed over the entire area of the mat. The blanket shall be covered on the top side with a heavyweight photodegradable polypropylene netting having ultraviolet additives to delay breakdown and an approximate 0.63 x 0.63 in (1.59 x 1.59 cm) mesh, and on the bottom side with a lightweight photodegradable polypropylene netting with an approximate 0.50 x 0.50 (1.27 x 1.27 cm) mesh. The blanket shall be sewn together on 1.50 inch (3.81 cm) centers with degradable thread. The blanket shall be manufactured with a colored thread stitched along both outer edges (approximately 2-5 inches [5-12.5 cm] from the edge) as an overlap guide for adjacent mats.

The SC150 shall meet Type 3.B specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17

Material Content		
<b>Matrix</b>	70% Straw Fiber	0.35 lbs/sq yd (0.19 kg/sm)
	30% Coconut Fiber	0.15 lbs/sq yd (0.08 kg/sm)
<b>Netting</b>	Top: Heavyweight photodegradable with UV additives	3 lbs/1000 sq ft (1.47 kg/100 sm)
	Bottom: lightweight photodegradable	1.5 lb/1000 sq ft (0.73 kg/100 sm)
<b>Thread</b>	Degradable	

Standard Roll Sizes			
<b>Width</b>	6.67 ft (2.03 m)	8 ft (2.4 m)	16.0 ft (4.87 m)
<b>Length</b>	108 ft (32.92 m)	112 ft (34.14 m)	108 ft (32.92 m)
<b>Weight ± 10%</b>	44 lbs (19.95 kg)	55 lbs (24.95 kg)	105.6 lbs (47.9 kg)
<b>Area</b>	80 sq yd (66.9 sm)	100 sq yd (83.61 sm)	192 sq yd (165.6 sm)

Index Property	Test Method	Typical
<b>Thickness</b>	ASTM D6525	0.35 in. (8.89 mm)
<b>Resiliency</b>	ECTC Guidelines	75%
<b>Water Absorbency</b>	ASTM D1117	342%
<b>Mass/Unit Area</b>	ASTM D6475	7.87 oz/sy (267.6 g/sm)
<b>Swell</b>	ECTC Guidelines	30%
<b>Smolder Resistance</b>	ECTC Guidelines	Yes
<b>Stiffness</b>	ASTM D1388	1.11 oz-in
<b>Light Penetration</b>	ASTM D6567	6.2%
<b>Tensile Strength - MD</b>	ASTM D6818	362.4 lbs/ft (5.37 kN/m)
<b>Elongation - MD</b>	ASTM D6818	29.4%
<b>Tensile Strength - TD</b>	ASTM D6818	136.8 lbs/ft (2.03 kN/m)
<b>Elongation - TD</b>	ASTM D6818	27.6%
<b>Biomass Improvement</b>	ASTM D7322	481%

Design Permissible Shear Stress	
<b>Unvegetated Shear Stress</b>	2.00 psf (96 Pa)
<b>Unvegetated Velocity</b>	8.0 fps (2.44 m/s)

Slope Design Data: C Factors			
Slope Gradients (S)			
<b>Slope Length (L)</b>	≤ 3:1	3:1 – 2:1	≥ 2:1
<b>≤ 20 ft (6 m)</b>	0.001	0.048	0.100
<b>20-50 ft</b>	0.051	0.079	0.145
<b>≥ 50 ft (15.2 m)</b>	0.10	0.110	0.190

NTPEP Large-Scale Slope  
ASTM D6459 - C-factor = 0.031

Roughness Coefficients – Unveg.	
<b>Flow Depth</b>	Manning's n
<b>≤ 0.50 ft (0.15 m)</b>	0.050
<b>0.50 – 2.0 ft</b>	0.050-0.018
<b>≥ 2.0 ft (0.60 m)</b>	0.018



North American Green  
5401 St. Wendel-Cynthiana Road  
Poseyville, Indiana 47633

nagreen.com  
800-772-2040

©2017, North American Green is a registered trademark. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.