

Mirafi® FW700



Mirafi® FW700 geotextile is composed of high-tenacity monofilament polypropylene yarns, which are woven into a stable network such that the yarns retain their relative position. Mirafi® FW700 geotextile is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). NTPEP Listed

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	370 (1647)	250 (1113)
Grab Tensile Elongation	ASTM D4632	%	15	15
Trapezoid Tear Strength	ASTM D4533	lbs (N)	100 (445)	60 (267)
CBR Puncture Strength	ASTM D6241	lbs (N)	950 (4228)	
			Minimum Roll Value	
Percent Open Area	COE-02215	%	4	
Permittivity	ASTM D4491	sec ⁻¹	0.28	
Flow Rate	ASTM D4491	gal/min/ft ² (l/min/m ²)	18 (733)	
			Maximum Opening Size	
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	70 (0.212)	
			Minimum Test Value	
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	90	

Physical Properties	Unit	Roll Size
Roll Dimensions (width x length)	ft (m)	12 x 300 (3.7 x 91)
Roll Area	yd ² (m ²)	400 (334)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi® is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

365 South Holland Drive
Pendergrass, GA 30567

Tel 706 693 2226
Tel 888 795 0808

Fax 706 693 4400
www.tencate.com

FGS000054
ETQR35



GAI-LAP-25-97